

Picchu Rio Gold Mining Co. SAC table

(Lab ID # L-02-60-01), show the existence of:

Zirconium	234,855.74 ppm	Scandium	49.99 ppm	Yttrium	568.74 ppm
Lanthanum	1,119.88 ppm	Cerium	2,521.34 ppm	Praseodymi	635.93 ppm
Samarium	279.97 ppm	Europium	30.72 ppm	Gadolinium	182.86 ppm
Terbium	167.10 ppm	Holmiun	60.47 ppm	Erbium	254.37 ppm
Thulium	86.31 ppm	Ytterbium	268.77 ppm	<u>Neodymium</u>	964.70 ppm
Dysprosium	1 96.54 ppm	Lutetium	24.08 ppm		